



Power of Desire



SOMANY

Somany Ceramics Limited : Noida: F-36, Sector-6; Ph.: 0120-4627900.

Ahmedabad: 601 to 606, 6th floor, Aalps Euphoria, Opp. Adani CNG Pump, B/s. Gota Flyover, S. G, Highway, Ahmedabad- 382481, Ph.: 079-27661103 & 04

Registered office: 2, Red Cross Place, Kolkata - 700001; Ph.(033) 22487406/5913

www.somanyceramics.com | e-mail marketing@somanyceramics.com

Toll Free No. 1800-103-0004 (Timing-10:00am to 6:30pm; Mon-Fri)



Visit us at:
www.somanyceramics.com



Find us at:
www.facebook.com/SomanyCeramic



Find us at:
www.twitter.com/SomanyCeramic



Find us at:
www.instagram.com/SomanyCeramics



MARVELA / CAT / JUNE 2023

MARVELA
FLORTUFF

SOMANY
Tiles | Bathware

ZAMEEN SE JUDEY

NEW
ARRIVAL

**MARVELA
FLOOR TILES**
COLLECTION

800x1600mm

PRODUCT LAUNCH

2023



UNIT - 3 | FOR ALL INDIA



Tiles Shown : GRAN WINONA DARK GREY FP &
GRAN WINONA LIGHT GREY FP

HD FULL POLISHED

800x1600mm
TILES COLLECTION



GRAIN GREYSON GREY HG



GRAIN SUTTON BLACK HG



GRAN ARKANA BEIGE FP



GRAN ARKANA LIGHT GREY FP




GRAIN SARAH BEIGE FP
ENDLESS



GRAIN SARAH NATURAL FP
ENDLESS




GRAN VERSUS CREMA FP




GRAN VERSUS BIANCO FP




GRAIN VALONIA GREY FP
ENDLESS



GRAIN VALONIA CREMA FP
ENDLESS



GRAN WINONA DARK GREY FP



GRAN WINONA LIGHT GREY FP



HD MATT CARVING


800x1600mm
TILES COLLECTION




GRAN CORMAC DARK BEIGE CR



GRAN CORMAC LIGHT GREY CR



GRAN DAVINA BIANCO CR




GRAN DAVINA BROWN CR



DESIGN, PATTERN & SHADE VARIATION GUIDE

Current development efforts have made ceramic tiles to resemble and look authentically identical to natural material (Stone, Wood, Fabric), and it has become increasingly difficult in many cases, to distinguish between two.

Recognising this situation, it is necessary to be informed on the grade of design & pattern variation that is expected from these products. As a general reference, the design & Pattern guide below classifies a scale of ranges according to the degree of variation.



V1 Uniform Appearance V2 Slight Variation V3 Moderate Variation V4 Substantial Variation

The classification is as follow:

V1 Minimal Variation V3 Random Variation V2 Slight Variation V4 Substantial Variation



High Definition Image

While laying the tiles please follow the arrow on the back of the tiles.
For removing the wax from the surface of the tiles please use the soft cotton cloth for rubbing with any boric/talk powder. And use with spacer to look good

PACKING DETAIL FOR UNIT-3 MARVELA TILES

Nominal Size	Thickness (mm)	Av. Wt. per carton (Kg)	No. of Tiles per carton	Coverage area per carton
800X1600mm (Gran Series)	9.0	53.0	2	2.56sq.mtr./27.55sq.ft.

TECHNICAL SPECIFICATION FOR UNIT-3 MARVELA TILES

Characteristics		Requirement as per IS 15622:2017 0.08 < E ≤ 3% Group B I b	Requirement as per ISO 13006: 2018 0.5 ≤ E ≤ 3% Group B I b	Our Value	Test Method
A	Dimension & Surface Quality				
i	Length & Width	± 0.1 %	±0.3%	± 0.1%	IS 13630 Part 1/ISO 10545-2
ii	Thickness	± 5.0 %	± 5.0%	± 4.0%	
iii	Straightness of Side	± 0.1 %	±0.3%	± 0.1%	
iv	Rectangularity	± 0.1 %	±0.3%	± 0.1%	
v	Surface Flatness				
a	Center curvature (%) (max.Deviation)	± 0.5 %	±0.4%	± 0.2%	
b	Edge curvature (%) (max.Deviation)	± 0.5 %	±0.4%	± 0.2%	
c	Corner warpage (%) (max.Deviation)	± 0.5 %	±0.4%	± 0.2%	
vi	Surface Quality	Min. 95 % of tiles will be free from visible defects	Min. 95 % of tiles will be free from visible defects	Min. 95 % of tiles will be free from visible defects	
B	Physical Properties				
i	Water Absorption (%)	Av. 0.08< E ≤ 3 %, Individual 3.3 max	Av. 0.5< E ≤ 3 %, Individual 3.3 max	Avg. E ≤ 3.0 %	IS 13630 Part 2/ISO 10545-3
ii	Modulus of Rupture [N/mm ²]	Avg. 30, Individual 27 Min	Avg. 30, Individual 27 Min	Avg. > 30	IS 13630 Part 6/ISO 10545-4
iii	Breaking Strength in N	Min. 1100	Min. 1100	Min. 1100	
iv	Moisture Expansion in mm/m	0.02	Test Method Available	0.02	IS 13630 Part 3/ISO-10545-10
v	Scratch Hardness of surface (Mohs)	Min 5	N.A	Min. 5 (for Matt), Min.3 (for Polished)	IS 13630 Part 13
vi	Resistance to Abrasion of glazed tiles(Class I to V)	Min II	Abrasion Class & Cycle passed	Class-V (for Matt), Class-III (for Polished)	IS 13630 Part 11/ISO 10545-7
vii	Coefficient of linear thermal expansion from ambient temperature to 100°C	7 X 10 ⁻⁶ K ⁻¹ max	Test Method Available	Max 6 X 10 ⁻⁶ K ⁻¹ Max	IS 13630 Part 4/ISO 10545-8
viii	Thermal Shock Resistance	10 cycle min	Test Method Available	10 cycle passed	IS 13630 Part 5/ISO-10545-9
ix	Crazing Resistance	4 cycle @ 7.5bar min	Required	4 cycle passed	IS 13630 Part 9/ISO 10545-11
x	Impact Resistance as Co-efficient of Restitution (COR)	0.55 Min	Test Method Available	Min 0.55	IS 13630 Part-14/ISO 10545-5
xi	Forst resistance	Required	Required	100 cycle passed	IS 13630 Part 10/ISO 10545-12
C	Chemical Resistance (Glazed Tiles)				
i	Stain Resistance	Min Class 1	Min Class 3	Min Class-1(For Matt), Min Class-2(for Polished)	IS 13630 Part 8 & ISO 10545-14
ii	Resistance to household chemicals	Min Class AA	Min B	Min Class AA	IS 13630 Part 8/ISO 10545-13
iii	Resistance to acids and alkalis (with exception of hydrofluoric acid and its compounds)	Required if agreed	Declared Value'	Min Class AA	

The reproduction of tiles in this catalogue is restricted to four color printing only and tiles are not in relative sizes, therefore customers are advised to see physical sample before placing the order. 'Technical Specifications' for Somany Wall & Floor Tiles are applicable only for premium quality tiles. Please inspect all tiles prior to installation, company will not entertain complaints, once the tiles are laid/fixed. Complaints will not be entertained for Borders, Highlighters & Motifs.