



SOMANY

Somany Ceramics Limited : Noida: F-36, Sector-6; Ph.: 0120-4627900. Ahmedabad: Office no. 7-14, 4th Floor, Aggarwal Mall, Opp. Sola Bhagwat Vidyapeeth, S.G. Road, Sola, Ph.: 079-66042500 to 599 Registered office: 2, Red Cross Place, Kolkata - 700001; Ph.(033) 22487406/5913 www.somanyceramics.com I e-mail marketing@somanyceramics.com

Toll Free No. 1800-103-0004 (Timing-10:00am to 6:30pm; Mon-Fri)











Available on the App Store Google play













2



Thickness 폱 15mm 800 x 2400 MM

Architectural Surfaces

FOR ALL INDIA UNIT-3

15mm Thickness

800x 2400mm *polished*

DURAGRES

EXCEED BOUNDARIES *with strong version*

We try to make every moment special and our space picture perfect. So, we bring you products that make your space look like its right out of a dream. We believe in turning your routine into experiences by giving it a special touch. Build a modern space with classic elegance and durability that leaves everyone in awe.


Fire Resistance





Heavy Duty Tile







FEATURES

The most important in tiles these modern times is the urgent need It is also resistant to water, heat, fire, chemical, impact for hygiene. These tile from DURAGRES are easy to clean providing and much more making it the ideal choice for any you with a germ-free surface.

space.

| \otimes | Antibacterial surface / Hygienic surface | | Lowest maintenance efforts |
|--|--|------|----------------------------|
| <u>, 0</u> | Liquid repellent and Water resistant | Mitz | Impact resistant |
| <u>></u> | Scratch resistant and Abrasion resistant | *** | Frost resistant |
| (i) | Chemical and Stain resistant | 222 | Fire resistant |
| $\bigcup_{i=1}^{n} \bigvee_{i=1}^{n} \bigcup_{j=1}^{n} \bigcup_{i=1}^{n} \bigcup_{j=1}^{n} \bigcup_{j=1}^{n} \bigcup_{j=1}^{n} \bigcup_{i=1}^{n} \bigcup_{j=1}^{n} \bigcup_{j$ | Resistant to bending | 555 | Heat resistant |

SOMANY? DURAGRES

EDGE BOOK



Micro bevel



Double straight squared edge



Squared edge at 45°



Double straight rounded edge

Half bullnose

Demi bullnose



Straight squared edge




Rounded edge at 45°



Rounded straight edge



Full bullnose





Birds beak





Soft corner













GRANIT TRIM 240 ALESSIA WHITE 15 SFP

Size - 800x2400mm Surface - Full Polish Thickness - 15mm Type - Full Body






GRANIT TRIM 240 COSMO CREMA 15 SFP

Size **- 800x2400mm** Surface **- Full Polish** Thickness **- 15mm** Type **- Full Body S&P**










GRANIT TRIM 240 COSMO GRIS 15 SFP

Size - 800x2400mm Surface - Full Polish Thickness - 15mm Type - Full Body S&P








GRANIT TRIM 240 COSMO BLACK 15 SFP

Size - 800x2400mm Surface - Full Polish Thickness - 15mm Type - Full Body S&P












GRANIT TRIM 240 COSMO BROWN 15 SFP

Size - 800x2400mm Surface - Full Polish Thickness - 15mm Type - Full Body S&P







GRANIT TRIM 240 CHOCO 15 SFP

Size - 800x2400mm Surface - Full Polish Thickness - 15mm Type - Full Body









GRANIT TRIM 240 GREY 15 SFP


Size - 800x2400mm Surface - Full Polish Thickness - 15mm Type - Full Body




SOMANY? DURAGRES

GRANIT TRIM 240 BLACK 15 GFP

Size **- 800x2400mm** Surface **- Full Polish** Thickness **- 15mm** Type **- Black Body PGVT**












GRANIT TRIM 240 WHITE 15 GFP

Size - 800x2400mm Surface - Full Polish Thickness - 15mm Type - White Body PGVT





GRANIT TRIM 240 ARIA CALACATTA 15 GFP

Size - 800x2400mm Surface - Full Polish Thickness - 15mm Type - White Body PGVT









GRANIT TRIM 240 OCEAN BLUE 15 GFP

Size **- 800x2400mm** Surface **- High Gloss** Thickness **- 15mm** Type **- Black Body PGVT**








GRANIT TRIM 240 ALEXANDRA BLUE 15 GFP

Size - 800x2400mm Surface - High Gloss Thickness - 15mm Type - Black Body PGVT
















GRANIT TRIM 240 LEPANTO MULTI 15 GFP

Size **- 800x2400mm** Surface **- High Gloss** Thickness **- 15mm** Type **- Black Body PGVT**












GRANIT TRIM 240 METALLO BLUE 15 GFP

Size **- 800x2400mm** Surface **- High Gloss** Thickness **- 15mm** Type **- Black Body PGVT**









GRANIT TRIM 240 IMP CLARION WHITE 15

Size **- 800x2400mm** Surface **- Carving** Thickness **- 15mm** Type **- Full Body with Carving**









GRANIT TRIM 240 IMP CLARION BLACK 15

Size **- 800x2400mm** Surface **- Carving** Thickness **- 15mm** Type **- Full Body with Carving**






TECHNICAL SPECIFICATION

DESIGN, PATTERN & SHADE VARIATION GUIDE

Current development efforts have made ceramic tiles to resemble and look authentically identical to natural material (Stone, Wood, Fabric), and it has become increasingly difficult in many cases, to distinguish between two.

Recognising this situation, it is necessary to be informed on the grade of design & pattern variation that is expected from these products. As a general reference, the design & Pattern guide below classifies a scale of ranges according to the degree of variation.





High Definition Image

While laying the tiles please follow the arrow on the back of the tiles.

For removing the wax from the surface of the tiles please use the soft cotton cloth for rubbing with any boric/talk powder

Notes

The reproduction of tiles in this catalogue is restricted to four color printing only and tiles are not in relative sizes, therefore customers are advised to see the physical sample before placing the order. "Technical Specification" for Somany wall & floor tiles are applicable only for premium quality tiles. Please inspect all tiles prior to installation. Company will not entertain complaints once tiles are laid/fixed. Complaints will not be entertained for Borders, Highlighters & Motifs.

| PACKING DETAIL FOR 800x2400MM 15MM GVT TILES | | | | | | | |
|--|------|---------------------------------|-------------------------|---------------------------|--|--|--|
| Nominal Size Thickness(mm) | | Average weight per carton (Kgs) | No. of tiles per carton | Coverage area per carton | | | |
| 800 x 2400 | 15.0 | 67.00 | 1 | 1.92sq.mtr. / 20.66sq.ft. | | | |

DURAGRES

| TECHNICAL SPECIFICATION FOR 800x2400MM 15MM GVT TILES | | | | | | | |
|--|--|---|---|---------------------------------|--|--|--|
| Characteristics | Requirement as per IS 15622 :2017 0.08 < E ≤ 3% Group Blb | Requirement as per ISO 13006:2018 ≤ 0.5% Group Bla | Our Values | Test Method | | | |
| A) Dimension & Surface Quality | | | | | | | |
| I) Length & Width | ± 0.1% | ± 0.3% | ± 0.1% | - | | | |
| ii) Thickness | ± 5.0% | ± 5.0% | ± 4.0% | | | | |
| iii) Straightness of Side | ± 0.1% | ± 0.3% | ± 0.1% | | | | |
| iv) Rectengularity | ± 0.1% | ± 0.3% | ± 0.1% | | | | |
| v) Surface Flatness | | | | IS 13630 Part 1/ ISO 10545-2 | | | |
| a) Center curvature (max.Deviation) | ± 0.5% | ± 0.4% | ± 0.2 % | | | | |
| b) Edge curvature (max.Deviation) | ± 0.5% | ± 0.4% | ± 0.2 % |] | | | |
| c) Corner warpage (max.Deviation) | ± 0.5% | ± 0.4% | ± 0.2 % | - | | | |
| vi) Surface Quality | Min. 95 % of tiles will be free from visible defects | Min. 95 % of tiles will be free from visible defects | Min. 95 % of tiles will be free from visible defects | | | | |
| B) Physical Properties | | | | | | | |
| I) Water Absorption | Av. 0.08 <e %,="" 3="" individual<br="" ≤="">3.3 max</e> | Av ≤ 0.5 %, Individual 0.6% max | Avg. E≤ 0.5 % | IS 13630 Part 2/ ISO 10545-3 | | | |
| ii) Modulus of Rupture [N/mm2] | Avg. 30, Individual 27 min | Avg 35, Individual 32 min | Avg. > 35 | IS 13630 Part 6/ISO 10545-4 | | | |
| iii) Breaking Strength in N | 1100 | 1300 | Min, 1300 | | | | |
| iv) Moisture Expansion in mm/m | 0.02 | Test Method Available | 0.02 | IS 13630 Part 3/ISO-10545-10 | | | |
| v) Scratch Hardness of surface (Mohs) | Min 5 | N/A | Min-5(for Matt & RT), Min.3(for Polished) | IS 13630 Part 13 | | | |
| vi) Resistance to Abrasion of glazed tiles(Class I to V) | Min II | Abrasion Class & Cycle passed | Class-V (for Matt & RT), Class - III(for polished) | IS 13630 Part 11 /ISO 10545-7 | | | |
| vii) Coefficient of linear thermal expansion from embiant temperature to 100° C | 7 X 10 ⁻⁶ K ⁻¹ max | Test Method Available | Max 6 X 10 ⁻⁶ K ⁻¹ max | IS 13630 Part 4/ ISO 10545-8 | | | |
| viii) Thermal Shock Resistance | 10 cycle min | Test Method Available | 10 cycle passed | IS 13630 Part 5/ISO-10545-9 | | | |
| ix) Crazing Resistance | 4 cycle @ 7.5bar min | Required | 4 cycle passed | IS 13630 Part 9/ISO 10545-11 | | | |
| x) Impact Resistance as Co-efficient of Restitution (COR) | 0.55 min | Test Method Available | Min 0.55 | IS 13630 Part 14/ISO 10545-5 | | | |
| xi) Frost Resistance | Required | Required | 100 Cycle Passed | IS 13630 Part 10/ISO 10545-12 | | | |
| C) Chemical Resistance (glazed Tiles) | | | | | | | |
| I) Stain Resistance | Min Class 1 | Min Class 3 | Min Class-1(For Matt), Class-2(for polished) | IS 13630 Part 8 &ISO 10545-14 | | | |
| ii) Resistance to household chemicals | Min Class AA | Min B | Min Class AA | | | | |
| iii) Resistance to acids and alkalis (with exception of hydrofluoric acid and its compounds) | Required if agreed | Declared Value ^r | Min Class AA | IS 13630 Part 8/ ISO 10545-13 | | | |